

ROTATIONAL MOLDING OF VINYL PLASTISOLS

The purpose of this document is to provide an overview of vinyl plastisol and starting points in setting up and running rotational molding of vinyl plastisol parts.

Polyethylene (PE), in general, is the largest polymer consumed in the rotational molding process. Vinyl plastisols differ from polyethylene in that they flow out and coat the inner mold surface until the gel temperature is reached. The gel temperature of a plastisol can be altered to facilitate the molding of certain shapes.

Vinyl powders differ in that the mass of material first distributes over the entire inner mold surface. As the mold is heated, it forms a skin and gradually melts to form a uniform layer of plastic.

The advantages of rotationally molding with vinyl plastisols are:

- Liquid form allows for ease of handling and the ability to easily meter small quantities, thus controlling inventory costs;
- Mold detail and finish replication is excellent;
- Readily pigmented and offers good color stability;
- Paints and top coat lacquers can be applied ;
(Note: Check with the supplier to be sure that the specific paint or lacquer utilized is compatible with vinyl.)
- Offers a wide range of properties (i.e. hardnesses, chemical resistance, etc.);
- Relatively low material cost compared to other materials.

Commonly produced parts from rotationally molded plastisol include:

- Hobby Horses (one of the first applications for rotationally molded plastisols);
- Playballs and Sport Balls (i.e. volleyballs, tetherballs, basketballs, etc.)
- Industrial Seating Components;
- Automotive Interior Components (i.e. crash pads, visors, arm rests, gear shift boots, etc.);
- Toys;
- Medical Devices and Models;
- Boat Bumpers;
- Miscellaneous Sporting Goods.

Specialty Coatings www.PolyOne.com

PolyOne Americas
33587 Walker Road
Avon Lake, Ohio 44012
United States
+1 440 930 1000

PolyOne Asia
Guoshoujing Road No. 88
Z.J Hi-Tech Park, Pudong
Shanghai, 201203, China
+86 (0) 21 5080 1188

PolyOne Europe
Rue Melville Wilson 2
5330 Assesse, Belgium
+32 (0) 83 660 211

PolyOne[™]

When selecting a vinyl plastisol for rotationally molding, in addition to hardness and environmental considerations, one should also consider other potential areas of performance, such as electrical performance, foamability, and the use of inserts (inserts should be primed prior to use) to maximize product acceptance.

Variables in vinyl plastisol rotational molding include:

- Part Shape,
- Ratio of Rotation,
- Speed of Rotation,
- Oven Temperature and Cycle Length,
- Cooling Spray, and
- Mold Temperature.

Part Shape

When first starting to run a plastisol without any processing direction, refer to the attached Rotation Ratio for Typical Shapes table. This table provides basic ratio starting points for many shapes.

Ratio of Rotation

Once the starting point ratio is decided, you are ready to set the controls. Generally, ratio of rotation is a function of Part Shape.

Most people become confused when calculating rotation ratio. The major axis is the inner shaft in the arm. The largest wheel located on the arm denotes the major. The minor axis is the outer shaft on the arm. The smaller wheel located nearest the oven denotes the minor. The major axis turns in the vertical plane and the minor axis turns in the horizontal plane.

It is important to remember, the ratio of rotation is a function of the shape being molded. A symmetrical shape, such as a round sphere or cube runs easily at a 4 to 1 ratio (major to minor axis rpm speed.). To set the ratios, determine the revolution per minute (rpm) of each axis. The rpm speed is easily determined by checking the time required, in seconds, to make one revolution of the major and minor drive shaft wheels (Major: largest wheel, Minor: smaller wheel). See the attached reference chart for converting how long it takes in seconds for one complete revolution to rpm. On most machines the dials indicating rpm are not accurate and it is best to manually check the rotation speed with a stopwatch.

With the speed (rpm) of each axis determined, the ratio of rotation can be calculated as follows:

$$\text{Ratio} = \frac{\text{Major Axis rpm}}{(\text{Minor Axis rpm} - \text{Major Axis rpm})}$$

For example, a Major Axis rpm of 8 and a Minor Axis rpm of 10 equals:

$$\text{Ratio} = \frac{8}{10 - 8} = \frac{8}{2} = \frac{4}{1}$$

In a situation where the Major axis is one-half the rpm of the minor axis, the ratio is 1 to 1. For example, the Major Axis rpm equals 5 and the Minor Axis rpm equals 10, the resultant rotation ratio is 1 to 1. The mold mounting shaft on the minor axis (horizontal plane) therefore rotates once for each rotation of the major axis (vertical plane). A rotational ratio of 1 to 1 is not recommended.

As the rpm speed of the Minor axis approaches that of the Major axis the ratio gets larger. For example, if the Major Axis rpm equals 8, and the Minor Axis rpm equals 10, the resultant rotation ratio equals 4 to 1. When the Major Axis rotation rpm equals 8, and the Minor Axis rpm equals 9, the rotation ratio equals 8 to 1. At a ratio approaching infinity, relative rotation stops.

To achieve reverse rotation, lower the Minor Axis rpm to a lower speed than the Major Axis rpm. For example, when the Major Axis rpm equals 8 and the Minor Axis rpm equals 6, the resultant rotational ratio is a negative 4 to 1.

In a negative ratio the spin is about the minor axis in the opposite direction. Negative rotation ratios tend to direct the flow more to the horizontal plane and causes poorer fill in complicated molds.

Speed of Rotation

Once the rotation ratio has been determined, the next consideration is the speed of rotation. Speed is simply how fast the major and minor axis wheels revolve in relation to rpm. For example, a Major Axis rpm of 8, and a Minor Axis rpm of 10 is a ratio of 4 to 1, whereas a Major Axis rpm of 12 and a Minor Axis rpm of 15 is also a 4 to 1 rotation ratio.

The speed of rotation is a function of vinyl plastisol viscosity and gel temperature. It is believed that a high gel temperature plastisol runs best at relatively slow rotation speeds. If the viscosity of the plastisol were low or thin, it would require increasing the speed of rotation. When the viscosity is high or thick, slow speeds would be best. The same effect is somewhat the same for lower gel temperature plastisols, viscosity, and running at faster speeds of rotation.

High speeds of rotation can cause problems because of the gyroscopic forces created. With large molds, this instability can result in machine damage.

Setting the speed of rotation and / or rotation ratio is accomplished by changing the pot settings on the machine panels. Increasing the pot setting increases the revolution speed and the rpm and vice-versa. With most machines, there is no correlation between how much a pot setting change will affect the rpm. Trial and error will be needed to determine the effect of any changes.

Seemingly minor pot setting changes may have drastic effects on ratio. To hold the ratio at a given reading requires adjusting both the major (inner shaft) and minor (outer shaft) proportionally.

Oven Temperature and Cycle Length

Generally, for the best vinyl plastisol distribution throughout the mold, lower temperatures and increased cycle times should be utilized. The entire plastisol mass must typically reach 350°F (177°C) for complete fusion to occur and optimum physical properties to be achieved. Complete fusion results in the development of ultimate physical properties.

Vinyl plastisols can be formulated to act differently under the same temperature / cycle time relationship. Some materials have a definite or sharp gel temperature and others are slower to react to temperature.

Trial and error will determine the highest temperature and shortest cycle time for an acceptable finished molded product. The balance of high oven temperatures, to achieve a quick cycle time, with the potential burning of the surface of the part, as observed through the development of a yellow or brownish tint on the surface of the part is critical.

Because plastisols gel (solidify) with heat, damper control is recommended on most all plastisol parts. When the damper is open, the heat blast from the oven burner potentially creates hot spots on the mold. By closing the damper for the first several minutes of the cycle, the plastisol will evenly distribute in the mold rather than gel faster on the hotter portion of the mold.

Cooling Spray

Many polymers used in rotational molding are sensitive to cooling cycles. These materials can often shrink uncontrollably when cooled too quickly. Fortunately, vinyl plastisols are not affected in this manner. However, cooling should be done in a manner so as not to damage molds as a result of rapid cooling of metal molds or result in corrosion of the cooling chamber.

A vinyl part will exhibit shrinkage. The shrinkage rate for vinyl will be approximately two percent from the mold dimensions and may vary as the vinyl plastisol formulation is changed.

If the article to be molded is difficult to strip form the mold, removal of the part is more easily accomplished with warm molds. Vinyl plastisol formulations can sometimes be compounded with raw materials to improve mold release performance. Commercially available mold release agents can also be utilized with difficult to remove parts. Testing should be conducted to insure that the mold release agent does not create any issues with the mold or the molded part.

Mold Temperature

When charging molds with plastisol, the best condition for molds is if they are at a temperature warm to the touch. If the molds are too hot when filled with plastisol, the plastisol can begin to gel on the mold surface resulting in poor plastisol distribution within the mold and an uneven part wall thickness. To eliminate this problem, increasing the length of the cooling spray to lower mold fill temperature is recommended. If a hot mold is required for easier part stripping, a higher gel plastisol may be required to get uniform distribution.

CONCLUSION

Trial and error will determine the best conditions under which to produce consistent rotationally molded vinyl plastisol parts. The rotomolder should use extreme care during the trial and error process as the burning of material in the mold may result in damage to the molds.

- Every shape to be molded has an optimum rotation ratio. Select a ratio that best describes the shape to be molded as a starting point.
- Speed of rotation with plastisols is important. When changing speed, remember to keep the rotation ratio constant. Plastisol gel temperature and viscosity are the major speed of rotation factors.
- Start with an oven temperature of 450°F (232°C) and a cycle long enough to achieve fusion. Fusion is best checked by examining a glossy air surface and / or by measuring for the development of ultimate physical properties. Faster production requires higher temperatures and shorter cycle times.
- Set the damper control to close for the first three minutes of the cycle. If the mold shape is not critical to oven heat blast, leave the damper open and shorten the oven cycle as a result of the hotter oven temperature.
- Set the cooling spray for a period of time so that the molds are warm to the touch when unloading.

Remember; select a ratio and a speed of rotation. Check and adjust the pot settings to the proper rpm. Most importantly, be sure the plastisol is fused properly by using a high enough temperature and long enough cycle time. Trial and Error will determine the best set of using conditions.

Each rotationally molded plastisol item has optimum settings for the best possible part.

Copyright © 2010, PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

Table 1: Rotation Ratios and Speeds for Typical Part Shapes

Shape	Rotation Ratio	Typical Speed (rpm)	
		Major Axis	Minor Axis
Oblongs and straight tubes ^a	8 to 1	8	9
Defroster ducts	5 to 1	5	6
Balls and gloves	4.5 to 1	8	9.75
Cubes, balls, odd shapes	4 to 1	8	10
Rectangular boxes, horses with bent legs	4 to 1	10	12.5
Shapes that have overlapping lines of rotation at 4 to 1	3.3 to 1	10 - 12	12.25 - 14.5
Rings, tires, balls	2 to 1	6	9
Rectangles that show two or more thin sides at 4 to 1	2 to 1	8	12
Picture frames, mannequins, round flat shapes	2 to 1	10	15
Horses with straight legs, auto crash pads ^b	1 to 3	12	18
Parts that have thin walls at 2 to 1	1 to 2	5 - 7	15 - 21
Flat rectangles, gas tanks, suit cases, tote bin covers	1 to 3	4	15
		6	22.5
		9.5	36
Tires, curved air ducts	1 to 4	4	20
Pipe angles, flat rectangles	1 to 4	5	25
Cylinders ^b , balls that have thin walls at 4 to 1	1 to 4	6	30
Cylinders ^b	1 to 5	4	24

^a Horizontally mounted, parallel to the major axis.

^b Vertically mounted, perpendicular to the major axis.

Table 2: Conversion Between RPM and Seconds per Rotation

RPM	Seconds per Rotation	RPM	Seconds per Rotation	RPM	Seconds per Rotation
1	60	9	6.6	17	3.53
1.25	48	9.25	6.5	17.25	3.48
1.5	40	9.5	6.3	17.5	3.43
1.75	34.3	9.75	6.15	17.75	3.39
2	30	10	6	18	3.33
2.25	26.7	10.25	5.85	18.25	3.29
2.5	24	10.5	5.71	18.5	3.24
2.75	21.8	10.75	5.58	18.75	3.2
3	20	11	5.45	19	3.16
3.25	18.5	11.25	5.33	19.25	3.12
3.5	17.1	11.5	5.21	19.5	3.07
3.75	16	11.75	5.1	19.75	3.04
4	15	12	5	20	3
4.25	14.1	12.25	4.9	21	2.85
4.5	13.3	12.5	4.8	22	2.72
4.75	12.6	12.75	4.7	23	2.6
5	12	13	4.6	24	2.5
5.25	11.4	13.25	4.5	25	2.4
5.5	10.9	13.5	4.44	26	2.3
5.75	10.4	13.75	4.36	27	2.2
6	10	14	4.28	28	2.14
6.25	9.6	14.25	4.21	29	2.06
6.5	9.2	14.5	4.14	30	2
6.75	8.88	14.75	4.06	31	1.93
7	8.57	15	4	32	1.87
7.25	8.27	15.25	3.9	33	1.82
7.5	8	15.5	3.87	34	1.76
7.75	7.74	15.75	3.8	35	1.71
8	7.5	16	3.75	36	1.66
8.25	7.27	16.25	3.69	37	1.62
8.5	7.05	16.5	3.63	38	1.57
8.75	6.85	16.75	3.58	39	1.53
				40	1.5

Table 3: Suppliers of Rotational Molding Equipment

The following list of companies provides just a few companies that produce equipment for rotational molding. This list was developed for the use of our customers only. The appearance of a supplier on this list does not constitute a recommendation by PolyOne Corporation, nor does the absence of a company constitute a lack of recommendation by PolyOne Corporation.

Alan Yorke Engineering Ltd.

Unit 4
Midland Business Centre
Bury Close, off Kimbolton Road
Higham Ferrers, Northants, NN10 8BE
England
Tel.: +44 (1933) 358219
Fax: +44 (1933) 410546

Caccia Engineering S.p.A.

Via Umberto Giordano, 1/13 (Cascina Elisa)
21017 Samarate (VA)
Italy
Tel.: +39 (0331) 707070
Fax: +39 (0331) 234021
[Website: www.cacciaeng.com](http://www.cacciaeng.com)

Ernst Reinhardt GmbH

Guterbahnhofstrasse 1
(P.O. Box 1880)
78008 Villingen Schwenningen
Germany
Tel.: + (7721) 8441-0
Fax: + (7721) 8441-44
ernst.reinhardt.gmbh@t-online.de

Ferry Industries, Inc.

4445 Allen Road
Stow, OH 44224-1093
USA
Tel.: (330) 920-4010
Fax: (330) 920-4200
Website: www.ferryindustries.com
ferrysales@ferryindustries.com

Fixopan

71, Nehru Place
110019 New Delhi
India
Tel.: +91 (129) 2237212
Fax: +91 (129) 2237672
directors@fixopan.org

Kann Manufacturing Corp.

210 Regent Street
P.O. Box 400
Guttenberg, IA 52052
Tel.: 563-252-2035
Fax: 563-252-3069

M. Plast India Ltd.

A-15, Sector-60 Phase III
Noida 201 307
Distt. Gautam Budh
Nagar (U.P.)
India
Tel.: +91 (120) 2581087
Fax: +91 (120) 2581090
[Website: www.mplast.com](http://www.mplast.com)

Polivinil Rotomachinery S.P.A.

Via Crosa 21/A
Cerano
Novara, 28065
Italy
Tel.: +39 (321) 772021
Fax: +39 (321) 772027
[Website: www.polivinil.com](http://www.polivinil.com)

Reinhardt Roto-Machines

7, First Floor, Panorma Complex
R.C. Dutt Road, Alkapuri
Vadodara
Gujarat, 390 007
India
Tel.: +91 (265) 2335489
Fax: +91 (265) 2340172
[Website: www.reinhardtindia.com](http://www.reinhardtindia.com)
[E-mail: rotoform@hotmail.com](mailto:rotoform@hotmail.com)

Roto-Tech, Inc.

220 Kreider Road
Palmyra, PA 17078
USA
Tel.: (717) 838-3955
Fax: (717) 838-4415

SAT

Savoie Hexapole 59
Rue Louis Armand
73420 Mery
France
Tel.: +33 (4) 79-717144
Fax: +33 (4) 79-617121
[Website: www.sat-thermique.com](http://www.sat-thermique.com)
sat@sat-thermique.com

S.T.P. Equipment Inc.

101 Industrial Boulevard
Bromptonville , QUE J0B 1H0
Canada
Tel.: 819-846-2787
Fax: 819-846-1280

Table 4: Suppliers of Molds for Rotational Molding

The following list of companies provides just a few companies that produce molds rotational molding. This list was developed for the use of our customers only. The appearance of a supplier on this list does not constitute a recommendation by PolyOne Corporation, nor does the absence of a company constitute a lack of recommendation by PolyOne Corporation.

Al-Cast Mold & Pattern, Inc.

15720 Lincoln Street Northeast
Ham Lake, MN 55304
USA
Tel.: (763) 434-4471
Fax: (763) 434-4624
[Website: www.al-castmold.com](http://www.al-castmold.com)
[E-mail: sales@al-castmold.com](mailto:sales@al-castmold.com)

Cole Industries, Inc.

2644 National Place
Garland, YX 75041
USA
Tel.: (972) 271-0280
Fax: (972) 278- 4515
[Website: www.coleindustries.com](http://www.coleindustries.com)
[E-mail: cole@coleindustries.com](mailto:cole@coleindustries.com)

JOHNDEL, Inc.

957 Tallmadge Rd.
Kent, OH 44240
USA
Tel.: (330) 677-4750
Fax: (330) 677-4847

Lakeland Mold Co.

1021 Madison St.
Brainerd, MN 56401
USA
Tel.: (218) 828-0110
Fax: (218) 829-8677

MAUS GmbH

Am Viehweg 9
D-76229 Karlsruhe
Germany
Tel.: +49 (721) 948740
Fax: +49 (721) 9487444
[Website: www.maus-gmbh.de](http://www.maus-gmbh.de)

Midwest Patterns Inc.

4901 North 12th St.
Quincy, IL 62305
USA
Tel.: (217) 228-6900
Fax: (217) 228-6906

Norstar Aluminum Molds, Inc.

W 66 N 622 Madison Avenue
Cedarburg, WI 53012
USA
Tel.: (262) 375-5600
Fax: (262) 375-5660

Persico S.p.A.

Via R. Follereau, 4
24027 Nembro - BG
Italy
Tel.: +39 (35) 4531811
Fax: +39 (35) 4531812
[Website: www.persico.com](http://www.persico.com)

Plasti-Cast Mold & Products Co.

1430 Archwood Avenue
Akron, OH 44306-3298
USA
Tel.: (330) 773-3377
Fax: (330) 773-3378
[Website: www.plasticast.com](http://www.plasticast.com)
[E-mail: info@plasticast.com](mailto:info@plasticast.com)

Rivers Metal Products, Inc.

3100 North 38th Street
Lincoln, NE 68504
USA
Tel.: (402) 467-9890
Fax: (402) 466-0937
[Website: www.riversmetal.com](http://www.riversmetal.com)

Trend Tooling, Los Angeles Division, Inc .

13226 Halldale Avenue
Gardena, CA 90249
USA
Tel.: (310) 323-4162
Fax: (310) 323-2434
[Website: www.trendtooling.com](http://www.trendtooling.com)

Troeger Metal Works, LLC

122 South Niles Avenue
South Bend, IN 46617
USA
Tel.: (574) 288-1483
Fax: (574) 287-7906

Wheeler Boyce Co.

4545 Boyce Pkwy
Stow, OH 44224
USA
Tel.: (330) 686-1292
Fax: (330) 686-1582

Table 5: Suppliers of Mold Release Agents for Rotational Molding

The following list of companies provides just a few companies that produce mold release agents for rotational molding. This list was developed for the use of our customers only. The appearance of a supplier on this list does not constitute a recommendation by PolyOne Corporation, nor does the absence of a company constitute a lack of recommendation by PolyOne Corporation.

Chem-Trend (Deutschland) GmbH

Robert-Koch-Strasse 27
D-22851 Norderstedt
Germany
Tel.: +49 (40) 529-550
Fax: +49 (40) 529-55111

Chem-Trend, Inc.

1445 West McPherson Park Dr.
P. O. Box 860
Howell, MI 48844
USA
Tel.: (517) 546-4520
Fax: (517) 546-8910

DuPont Coating & Release Systems

8193 Windham Street
Garrettsville, OH 44231
USA
Tel.: (330) 527-9939
Fax: (330) 527-7719
[Website: www.dupont.com/releasesystems](http://www.dupont.com/releasesystems)

Henkel Technologies

1001 Trout Brook Crossing
Rockey Hill, CT 06067
USA
Tel.: (860) 571-5100
Fax: (860) 571-5475

Matrix Polymers Limited

22/40 Tenter Road
Moulton Park Industrial Estate
Northamptonshire NN3 6AX
England
Tel.: +44 (8707) 497733
Fax: +44 (8707) 497744

McLube Division, McGee Industries, Inc.

9 Crozerville Road
P.O. Box 2425
Aston, PA 19014-0425
USA
Tel.: (610) 459-1890
Fax: (610) 459-9538
[Website: www.mclube.com](http://www.mclube.com)