

## SLUSH MOLDING PROCESS

Slush molding is an excellent method of producing open, hollow objects, including rain boots, shoes, toys, dolls and automotive products, such as protective skin coatings on arm rests, head rests and crash pads. The basic process of slush molding involves exposing a hollow mold to heat, filling a hollow mold with vinyl plastisol or vinyl powder compound, gelling an inner layer or wall of plastisol or partially fused powder compound in the mold, inverting the mold to pour out the excess liquid plastisol or unfused powder compound and then heating the mold again to fuse the vinyl compound which remains in the mold. The mold is then cooled and the finished part is removed.

Slush molding can be a simple hand operation for limited production, or an elaborate conveyerized system for long runs. This process can be a one pour method, where finished or semi-finished products can be made by one slushing step, or a multiple-pour method where two or more slushing steps are used.

The wall thickness of the slush molded part, made from powder compound at a given oven temperature, is determined by several factors: the thickness of the metal wall of the mold, the length of time the mold is preheated, and the amount and type of plasticizer in the compound. Molds used in slush molding are produced from spun, machined or electroformed aluminum. Vinyl powder compound will reproduce the surface finish of the mold, whether matte or glossy. Mold porosity, depending upon severity, may cause such detrimental effects as surface gloss reduction, pinholing, and voids in the molded part.

Copyright © 2010, PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the Information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the Information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the Information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the Information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the Information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the Information or products reflected by the Information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.

PolyOne Corporation / 33587 Walker Road, Avon Lake, Ohio 44012

TAB-SC007 10-2010

### Specialty Coatings [www.PolyOne.com](http://www.PolyOne.com)

PolyOne Americas  
33587 Walker Road  
Avon Lake, Ohio 44012  
United States  
+1 440 930 1000

PolyOne Asia  
Guoshoujing Road No. 88  
Z.J Hi-Tech Park, Pudong  
Shanghai, 201203, China  
+86 (0) 21 5080 1188

PolyOne Europe  
Rue Melville Wilson 2  
5330 Assesse, Belgium  
+32 (0) 83 660 211

**PolyOne**<sup>™</sup>