



## Stan-Tone™ Colorants Water Dispersion (WDN)

Stan-Tone™ WDN water dispersions are high-solids organic and inorganic single pigment dispersions designed to help meet industry standards, including pH level. They are produced to provide consistent color value and tint strength. These products contain alkali-stabilized acrylic resin, pigments, water and a small amount of nonmetallic preservative.

### KEY CHARACTERISTICS

- No wetting agents, no surfactants, no glycol
- Consistent tint strength and color
- Minimized settling

### APPLICATIONS

Stan-Tone WDN dispersions are suitable for use in a variety of applications, including:

- Latex gloves and dipped balloons
- Coating and adhesive systems



Stan-Tone Code	Pigment Type	Approx. % Pigment	Approx. % Solids	Color Index	pH Typical	Weight Lbs/Gal
<b>WHITE</b>						
10WDN03	Titanium Dioxide, Rutile	60	73	PW-6	9	16.7
<b>YELLOW</b>						
12WDN01	Diarylide AAOT GS	35	43	PY-14	8.8	9.4
12WDN02	Diarylide HR RS	37	44	PY-83	8.8	9.6
12WDN03	Arylide GY RS	38	45	PY-74	8.8	9.2
81WDN01	Iron Oxide	55	63	PY-42	8.8	14.5
<b>ORANGE</b>						
15WDN01	Pryazolone YS	40	45	PO-13	8.8	9.2
15WDN03	Dianisidine RS	35	37	PO-16	8.8	9.2
15WDN06	DNA Orange RS	31	43	PO-5	8.8	9.7
<b>RED</b>						
22WDN01	Lithol Rubine BS	33	40	PR-57	8.8	9.8
21WDN01	Naphthol BS	35	43	N/A	8.8	9.5
25WDN01	Red 2B, Ca BS	34	41	PR-48:2	8.8	9.6
28WDN01	Red 2B, Ba YS	36	44	PR-48:1	8.8	9.5
82WDN02	Iron Oxide	57	66	PR-101	8.8	16
<b>BLUE</b>						
40WDN01	Phthalocyanine RS	35	46	PB-15	8.8	9.7
40WDN03	Phthalocyanine GS	38	43	PB-15:3	8.8	9.8
<b>GREEN</b>						
WDN-27822	Phthalocyanine BS	42	53	PG-7	8.8	10.5
<b>VIOLET/MAGENTA</b>						
24WDN02	Carbazole	35	48	PV-23	8.8	9.6
24WDN03	Quinacridone	31	39	PV-19	8.8	9.6
24WDN05	Quinacridone	30	41	PR-122	8.8	10
<b>BLACK</b>						
90WDN01	Carbon Black	45	49	PB-7	8.8	9.3

**WDN**

RS = Red Shade

YS = Yellow Shade

BS = Blue Shade

GS = Green Shade

HR = Heat-Resistant

[www.polyone.com](http://www.polyone.com)



Copyright © 2019, PolyOne Corporation. PolyOne makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. PolyOne makes no warranties or guarantees respecting suitability of either PolyOne's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. POLYONE MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.